

Fiber By-Products Corp.
61801 C.R. 127
Coshen, Indiana 46528

Client Project ID:
Purchase Order #:
Page: 1 of 1


Attn: Cory M. Schrock

Analytical Report

Sample Log No:	10C4336	Sample Recognized As:	Wood Pellets
Sample Reference:	Pro Pellets	Arrival Date:	11/29/2010
Sample Designation:	Bag 1	Analyzed Date:	12/8/2010
Sample Date / Time:		Report Date Version:	12/9/2010 9:03
		Report ID:	10C4336-01

	METHOD	UNITS	MOISTURE FREE	AS RECEIVED
Moisture Total	ASTM E871	wt. %		3.59
Ash	ASTM D1102	wt. %	0.43	0.41
Sulfur	ASTM D4239	wt. %	0.627	0.604
Gross Cal. Value at Const. Vol.	ASTM E711	Btu/lb	8573	8265
Chlorine	ASTM D6721	mg/kg	146	141
Bulk Density	ASTM E873	lbs/ft ³		44.50
Fines (Less than 1/8")	TPT CH-P-06	wt. %		0.14
Durability Index	Kansas State	PDI		98.6
Sample Above 1.50"	TPT CH-P-06	wt. %		0.0
Maximum Length (Single Pellet)	TPT CH-P-06	inch		1.57
Diameter, Range	TPT CH-P-05	inch	0.253 to 0.259	
Diameter, Average	TPT CH-P-05	inch		0.256
Bag Weight	TPT CH-P-01	lbs		40.2

Sampling was not performed by Twin Ports Testing, Inc.
This test report shall not be reproduced except in full, without written approval of Twin Ports Testing, Inc.
The reported analytical results relate only to the sample submitted.

Signed: 
Joshua Stern, Chemistry Lab Manager

Date: 12/9/10