

Fiber By-Products Corp.  
 61801 C.R. 127  
 Goshen, Indiana 46528

**Date Received:** 5/12/2010

**Date Tested:** 5/13/2010

**Purchase Order #:**
**Attn:** Cory M. Schrock

**Sample Log Number:** 10C1839

**Sample Designation:** 40Lb. "Pro Pellet" Bag

	MOISTURE & ASH FREE	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Moisture Total			2.70	% wt.	ASTM E871
Ash		0.42	0.41	% wt.	ASTM D1102
Sulfur		0.011	0.010	% wt.	ASTM D4239
Heating Value	8467	8432	8204	Btu/lb	ASTM E711

	MDL	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Chlorine	10	42	41	mg/kg	ASTM D6721

	AS RECEIVED	UNITS		AS RECEIVED	UNITS
Bulk Density	46.57	lbs/cu.ft.	Fines	0.20	% wt.
Sample Above 1.50 In	0.0	%	Durability Index	97.6	
Maximum Length	1.925	inch	Stated Bag Wt.	40.0	lbs
Diameter, Range	0.247 to 0.261	inch	Actual Bag Wt.	40.0	lbs
Diameter, Average	0.252	inch			

 Prepared By: *Kevin Anderson*

 Date: 5/18/10